

Quality: B 1017

Date: Sep 03

Properties	Test Standards		Values	Units
Fibre Type of the Base Fabric Faserstoff des Trägergewebes Tissu Support	(DIN 60001)		PES Lowick	
Yarn Count Fadendichte Nombre de Fil	(DIN EN 1049)	warp weft	8 8,5	yarn/cm
Titer of Yarn Garn Titer Titres du fil			1100	dtex
Weave Style Bindung Armure	(DIN ISO 9354)		L 1/1	
Weight per Unit Area of Base Fabric Flächenbezogene Masse des Gewebes Poids du Tissu Support	(DIN EN 12127)		180	g/m²
Base Coat Beschichtungsart Nature de l'Énduit			PVC, fungicide PVC, fungizid PVC fungicide	
Top Coat Schlußlack Équipement de Surface			acrylic lacquer Acryllack laque acrylique	
Total Mass per Unit Area Flächenbezogene Gesamtmasse Masse Totale	(DIN EN ISO 2286-2)		650	g/m²
Width Breite Largeur	(DIN EN ISO 2286-1)		250 300 (white)	cm
Tensile Strength Höchstzugkraft Resistance à la Rupture en chaine/en trame	(DIN 53354)	warp weft	2800 2500	N/5cm
Tear Resistance Weitereißkraft Resistance à la Déchirure en chaine/en trame	(DIN53363)	warp weft	300 300	N
Adhesion Haftung Adhesion	(DIN 53357)			N/5cm
Remarks Bemerkungen Remarques	tents, Zeltdachware, tentes DIN 4102 B1, BS 5438/7837, SIS 65 00 82, Cal. Fire Marshall, AWTA 67931, CL 2, NFP 92503, M 2			