

**Quality: B 1088**

**Date: Feb 04**

Properties	Test Standards		Values	Units
<b>Fibre Type of the Base Fabric</b> Faserstoff des Trägergewebes Tissu Support	(DIN 60001)		PES	
<b>Yarn Count</b> Fadendichte Nombre de Fil	(DIN EN 1049)	warp weft	9 9	yarn/cm
<b>Titer of Yarn</b> Garn Titer Titres du fil			1100	dtex
<b>Weave Style</b> Bindung Armure	(DIN ISO 9354)		L 1/1	
<b>Weight per Unit Area of Base Fabric</b> Flächenbezogene Masse des Gewebes Poids du Tissu Support	(DIN EN 12127)		210	g/m <sup>2</sup>
<b>Base Coat</b> Beschichtungsart Nature de l'Énduit			PVC both sides beids. PVC PVC deux côtés	
<b>Top Coat</b> Schlußlack Équipement de Surface			PU both sides beids. PU PU deux côtés	
<b>Total Mass per Unit Area</b> Flächenbezogene Gesamtmasse Masse Totale	(DIN EN ISO 2286-2)		700	g/m <sup>2</sup>
<b>Width</b> Breite Largeur	(DIN EN ISO 2286-1)		265	cm
<b>Tensile Strength</b> Höchstzugkraft Resistance à la Rupture en chaine/en trame	(DIN 53354)	warp weft	3000 3000	N/5cm
<b>Tear Resistance</b> Weitereißkraft Resistance à la Déchirure en chaine/en trame	(DIN53363)	warp weft	300 300	N
<b>Adhesion</b> Haftung Adhesion	(DIN 53357)		100	N/5cm
<b>Remarks</b> Bemerkungen Remarques	container, Behälter, conteneurs, limited food grade, bed. Lebensmittelbest., limité alimentaire flexible tanks tested for food approval by Dr. Rothe			