

Quality: B 1915**2A****Type III****Date: Sep 03**

Properties	Test Standards		Values	Units
Fibre Type of the Base Fabric Faserstoff des Trägergewebes Tissu Support	(DIN 60001)		PES	
Yarn Count Fadendichte Nombre de Fil	(DIN EN 1049)	warp weft	10,5 10,5	yarn/cm
Titer of Yarn Garn Titer Titres du fil			1670	dtex
Weave Style Bindung Armure	(DIN ISO 9354)		P 2/2	
Weight per Unit Area of Base Fabric Flächenbezogene Masse des Gewebes Poids du Tissu Support	(DIN EN 12127)		370	g/m ²
Base Coat Beschichtungsart Nature de l'Énduit			PVC, fungicide PVC, fungizid PVC, fungicide	
Top Coat Schlußlack Équipement de Surface			acrylic lacquer Acryllack laque acrylique	
Total Mass per Unit Area Flächenbezogene Gesamtmasse Masse Totale	(DIN EN ISO 2286-2)		1100	g/m ²
Tensile Strength Höchstzugkraft Resistance à la Rupture en chaine/en trame	(DIN 53354)	warp weft	5750 5000	N/5cm
Tear Resistance Weitereißkraft Resistance à la Déchirure en chaine/en trame	(DIN53363)	warp weft	950 800	N
Adhesion Haftung Adhesion	(DIN 53357)		120	N/5cm
Translucency at 550 nm Transluzenz bei translucidite	(DIN 5036)			%
Fire behaviour according to Brandverhalten entspricht ignifuge selon	DIN 4102 B1, BS 5438, AWTA AS 1530, CL2,			