

Nahtfestigkeiten verschiedener Plakatwandqualitäten bei Raumtemperatur in Anlehnung an DIN 53354 (Nahtbreite 25mm)

Seam strength of different sign materials at room temperature following DIN 53354 (seam width 25mm)

Qualität / Quality		N/5cm	lb/in
B 3127	mesh premium	1749	200
B 3124	mesh supreme	1335	152

Qualität / Quality		N/5cm	lb/in
B 3112	frontlit premium	2636	300
B 3944	frontlit supreme	2520	287

Qualität / Quality		N/5cm	lb/in
B 3727	backlit premium	2665	304
B 3949	backlit supreme	2810	320

Verseidag Indutex GmbH
- seemee® -

Krefeld, 01.07.2002