

Ref: 7658/2/STC004

Page 1 of 2

Date: 1 August 2001

Client: Verseidag seemee UK Ltd
Collingwood House
Alington Road
Eynesbury
St. Neots
Cambridgeshire
PE19 6YH

Job title: Flammability testing of one PVC-coated material

Client's order or ref no: Letter 25 July 2001

Date of receipt: 27 July 2001

Description of sample(s): One PVC-coated material
Reference B3124024, Batch 170103Work requested: Flammability testing according to BS 5867: Part 2: 1980
Type B performance requirements

Ref: 7658/2/STC004 Page 2 of 2

Client: Verseidag seemee UK Ltd

Sample: One PVC-coated material
Reference B3124024, Batch 170103

Performance Standard: BS 5867: Part 2: 1980
Type B performance requirements

Test Method: BS 5438: 1976 Test 2
Flame application time = 15s

Pretreatment: None (tested in the "as received" condition)

Summary of Results:

"The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration."

Specimen	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No
Duration of flaming, s	0	0	0	0	0	0
Duration of afterglow, s	0	0	0	0	0	0
Vertical hole size, mm	124	103	123	145	130	131
Horizontal hole size, mm	18	18	20	20	19	19

Assessment:

Tested in the "as received" condition this PVC-coated material complies with the Type B performance requirements of BS 5867: Part 2: 1980.

Reported by: *M T Healey* M T Healey

Countersigned: *P M Eaton* P M Eaton

Opinions and interpretation expressed herein are outside the scope of UKAS accreditation.
Enquiries concerning this report should be addressed to Customer Services.